## ABSTRACT OF THE DISCLOSURE

The stripping agent is sprayed from the tip of the nozzle 33 onto the wafer surface, while the first supply nozzle 33 is actuated to scan from the central portion of the wafer to the outer 5 portion thereof. This operation provides the situation, in which the interface of the residual droplet 38 is pulled back from the center of the wafer to the outer portion of the wafer by the surface tension of the stripping agent supplied from the nozzle. Meanwhile, the second supply nozzle 36 also scans at a same scanning speed 10 as the first supply nozzle 33 scans. Vapor IPA is sprayed from the orifice of the second supply nozzle 36. This provides that vapor IPA is sprayed onto the wafer surface immediately after the stripping agent is sprayed thereon from the first supply nozzle 15 33, and the residual stripping agent on the wafer surface is efficiently replaced with IPA.